

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



AW

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ :

D06M 16/00 // 101:12

A1

(11) International Publication Number:

WO 99/60200

(43) International Publication Date: 25 November 1999 (25.11.99)

(21) International Application Number: PCT/US99/10496

(22) International Filing Date: 12 May 1999 (12.05.99)

(30) Priority Data:

09/082,218

20 May 1998 (20.05.98)

US

09/159,182

23 September 1998 (23.09.98)

US

(71) Applicant: NOVO NORDISK BIOCHEM NORTH AMERICA, INC. [US/US]; 77 Perry Chapel Church Road, Franklinton, NC 27525 (US).

(72) Inventors: MCDEVITT, Jason, Patrick; 3651 Sleepy Hollow Road, Wake Forest, NC 27587 (US). WINKLER, Jakob; Sofienhøjvej 16, 1.t.v., DK-2300 København S (DK).

(74) Agents: ZELSON, Steve, T. et al.; Novo Nordisk of North America, Inc., Suite 6400, 405 Lexington Avenue, New York, NY 10174 (US).

(81) Designated States: AE, AL, AU, BA, BB, BG, BR, CA, CN, CU, CZ, EE, GD, GE, HR, HU, ID, IL, IN, IS, JP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, UZ, VN, YU, ZA, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published

With international search report.

(54) Title: A METHOD FOR ENZYMIC TREATMENT OF WOOL

(57) Abstract

A method of treating wool, wool fibers or animal hair with a proteolytic enzyme and a transglutaminase. The described method results in improved shrink-resistance, handle, appearance, wettability, reduction of felting tendency, increased whiteness, reduction of pilling, improved softness, tensile strength retention, improved stretch, improved burst strength, and improved dyeing characteristics such as dye uptake and dye washfastness. Furthermore, relative to treatments with proteolytic enzymes alone (no transglutaminase), the described method results in reduced weight loss, reduced fiber damage, and improved strength.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

A METHOD FOR ENZYMATIC TREATMENT OF WOOL

FIELD OF THE INVENTION

The present invention relates to a method of treating wool, wool fibers or animal hair with a transglutaminase and a proteolytic enzyme.

BACKGROUND OF THE INVENTION

Two major problems associated with wool are its tactile discomfort (itchiness) and tendency to shrink. Improvements in softness and handle of wool can be achieved by addition of various chemical agents such as silicone softeners or by addition of proteolytic enzymes. The cost of these improvements may be greater than the moderate benefits achieved. Changes in one property of wool can affect other properties, sometimes adversely. For example, protease treatments normally have adverse effects on strength and weight of wool material.

Methods to generate shrink-resistant wool are known. The most commonly used method is the IWS/CSIRO Chlorine Hercosett process, which comprises an acid chlorination of wool, followed by a polymer application. This process imparts a high degree of shrink-resistance to wool, but adversely affects the handle of wool, and generates environmentally damaging waste.

Methods to reduce shrinkage of wool which do not result in release of damaging substances to the environment have been suggested, including enzymatic processes as well as benign chemical processes such as low-temperature plasma treatments. Plasma treatment is a dry process which involves treating wool fiber material with electrical gas discharges (so-called plasma). At present, there are obstacles (cost, capacity, compatibility) to large-scale commercialization of a plasma treatment process.

Various enzymatic methods have been used to treat wool. JP-A 51099196 describes a process to treat wool fabrics with alkaline proteases. JP-A 3213574 describes a method to treat wool using transglutaminase (an enzyme naturally found in wool follicles from sheep) or a solution containing transglutaminase. WO 98/27264 describes a method for reducing the shrinkage of wool comprising contacting wool with an oxidase or a peroxidase solution under conditions suitable for reacting the enzyme with wool. US 5,529,928 describes a process for obtaining a wool with a soft woolly handle and shrink-resistant

properties by using an initial chemical oxidative step or an enzyme treatment (e.g. a peroxidase, a catalase, or a lipase) followed by a protease treatment, followed by heat treatment. EP 358386 A2 describes a method to treat wool which comprises a proteolytic treatment and one of or both an oxidative treatment (such as NaOCl) and a polymer treatment. EP 134267 describes a method for treating animal fibers with an oxidizing agent, followed by a proteolytic enzyme in a salt-containing composition.

The environmental and performance deficiencies associated with current industrial processes for wool treatment substantiate the need for novel processes that provide further improvements relating to shrink-resistance or softness. Enzymatic methods for treating wool, used alone or in conjunction with an oxidative chemical step, have had little commercial value, a fact that is attributable to their relatively high costs and their tendency to damage wool by causing weight and strength losses. There is a need for an improved enzymatic method to treat wool, wool fibers, or animal hair material which imparts improvements in softness, shrink-resistance, appearance, whiteness, dye uptake, and resistance to pilling, but causes less fiber damage than known enzymatic treatments.

SUMMARY OF THE INVENTION

The object of the present invention is to provide improved enzyme-based methods for treating wool, wool fibers or animal hair, in particular methods which provide advantages with regard to improved shrink-resistance, and/or improvements of softness and handle which are highly desired by the end-user, while minimizing fiber damage relative to existing degradative treatments of wool and other animal hair materials.

The invention relates to a method of treating wool, wool fibers or animal hair, comprising contacting the wool, wool fibers or animal hair in aqueous solution with a proteolytic enzyme, either preceding or, preferably, simultaneously with a transglutaminase.

The scalar structure of wool is responsible to a large degree for many of its properties, both good and bad, and is primarily responsible for wool's tendency to shrink. One way to achieve shrink-resistance is to remove the scales from the surface of wool. This process is not industrially practical for a number of reasons, in particular the extreme strength and weight losses that occur. An ideal commercial process for imparting shrink-resistance would necessarily alter the physical structure of the fiber surface without

significantly weakening the fiber. Unfortunately, many methods that alter the scale structure (including conventional proteolytic enzyme treatment) do so via destructive means. At the molecular level, chemical bonds are ruptured, causing molecular weight degradation of the proteins. This molecular weight breakdown is responsible for the macroscopically observed reduction in strength and weight of the wool or animal hair textiles.

The present invention describes a method that uses two complementary enzymes to substantially modify the surface structure of the fiber while also minimizing degradation. Proteolytic enzymes cleave amide bonds, while transglutaminases form amide bonds, albeit different ones. In the context of the present invention, proteolytic enzymes are primarily responsible for breaking down the surface structure, while transglutaminases aid in that process, and also prevent the excessive molecular weight breakdown associated with proteolytic enzyme treatments. Consequently, relative to conventional proteolytic treatments, the treatments described in the present invention provide superior shrink-resistance, with reduced fiber damage. Other benefits are also achieved, either relative to untreated wool, wool treated with proteolytic enzymes, or wool treated with transglutaminases.

Depending on the particular characteristics of the wool subjected to the treatment according to the present invention, the benefits resulting from this treatment can be improved shrink-resistance, improved handle, improved appearance, improved wettability, reduction of felting tendency, increased whiteness, reduction of pilling, improved softness, tensile strength retention, improved stretch, improved burst strength, and improved dyeing characteristics such as dye uptake and dye washfastness. Furthermore, this combination reduces fiber damage, as manifested by reductions in fabric weight loss and burst strength, relative to protease treatments alone.

In a further embodiment, the wool, wool fibers or animal hair may have undergone an oxidative pre-treatment prior to any of the enzymatic treatments described above. Examples of oxidative pre-treatments include acidic chlorination, DCCA, sodium hypochlorite, caroat, and permanganate, as well as enzymatic treatments using oxidoreductases such as peroxidase or haloperoxidase.

DETAILED DESCRIPTION OF THE INVENTION

Before the methods of the invention are described, it is to be understood that this invention is not limited to the particular methods described. The terminology used herein is for the purpose of describing particular embodiments only, and is not intended to be limiting since the scope of the present invention will be limited only by the appended claims.

As used in this specification and the appended claims, the singular forms "a", "an", and "the" include plural references unless the context clearly dictates otherwise. Thus, for example, references to "proteolytic enzyme" or "proteolytic preparation" include mixtures of such proteolytic enzymes, reference to "the method" includes one or more methods, and/or steps of the type described herein and/or which will become apparent to those persons skilled in the art upon reading this disclosure and so forth.

Unless defined otherwise, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which the invention belongs. Although any methods and materials similar or equivalent to those described herein can be used in the practice or testing of the present invention, the preferred methods and materials are now described. All publications mentioned herein are incorporated herein by reference for the purpose of disclosing and describing the material in connection with which the reference was cited.

Definitions

The term "shrinkage" refers to the felting shrinkage of fibers as defined in IWS TM 31, i.e., felting shrinkage is the irreversible shrinkage caused by progressive entanglement of the wool fibers induced by washing in an aqueous solution, and is defined as the reduction in length and/or width induced by washing. Shrinkage can be measured in accordance with IWS TM 31, or it can be measured using the following modification. Wool samples (24 cm x 24 cm) are sewed around the edges and inscribed with a rectangle (18 cm x 18 cm). Samples are treated, air-dried, then subjected to five cycles of machine washing and drying (warm wash, high heat of drying) in combination with external ballast such as towels and articles of clothing. The dimensions of the rectangle are measured after five cycles, and the shrinkage is defined as the change in dimensions of the rectangle, after accounting for initial relaxation shrinkage.

A reduction in shrinkage implies a reduction in felting, and thus all methods that

provide improved shrink-resistance also provide "anti-felting" properties.

The term "handle" is a subjective term that refers to the sensation of touch or feel of a textile. The term "softness" is a subjective term referring to the feel of a textile, and is a component of handle.

The term "pilling" refers to the entangling of fibers into balls (pills), which are visible on the surface of a fabric. A pill is of sufficient density that it will cast a shadow. Resistance to pilling can be measured according to IWS Test Method 196, or can be inspected visually. Pilling is a major component of fabric appearance (along with other properties such as whiteness). Reduced pilling gives better appearance and improved resistance to pilling is implied herein wherever the term "superior appearance" is used.

The term "stretch" refers to the increase in length of a fibrous material when a fixed load is applied. In general, a higher value for stretch is preferred relative to a lower value. In the present context, the term "elongation" refers to the permanent increase in length (non-recoverable extension) of a fibrous material after application and removal of a fixed load. In general, a lower value for elongation is preferred relative to a higher value. Stretch and elongation have been measured in accordance with the following modification of IWS TM 179. Fabric strips (100 mm x 55 mm rectangles, with the longer dimension in the weft direction) were placed in the jaws of a suitable tensile strength machine such as an Instron® 5564. The distance between the jaws was set at 60 mm, and the load was increased to 10N at a rate of extension of 100 mm/min. Once the desired load was reached, the direction of movement was immediately reversed, and the rate of contraction was equal to the rate of extension. Five cycles were performed. The extension after the first cycle was defined as the fabric "stretch", and the "elongation" was defined as the stretch after the fifth cycle relative to the stretch after the first cycle, i.e., $E = S_5/S_1$.

The term "whiteness" is intended to mean a optical determination of the extent of color on wool. Whiteness can be measured in Stensby units ($W = L + 3a - 3b$) on a suitable spectrophotometer such as the Macbeth Color-Eye® 7000.

The term "burst strength" refers to the pressure applied to a circular specimen in distending it to rupture. Burst strength can be measured (using a suitable apparatus such as the Mullen® tester from B.F. Perkins) in accordance with IWS TM 29, and can be performed on either wet or dry fabric.

The term "dyeing characteristics" refers to properties associated with dyeing of

wool or animal hair material, including dye uptake and dye color fastness to wet alkaline contact (as defined in IWS TM 174). Dye uptake is a measure of the capacity of wool or animal hair material immersed in a dye solution to absorb available dyestuff. This property can be measured by the following test. In a suitable reaction vessel, wool or animal hair material is added to a buffered solution of acid black 172 (300 ml of 0.05 M NaOAc buffer, pH 4.5, plus 7.5 mL of a 1.0% w/w solution of acid black 172 in water). The vessel is incubated in a shaking water bath at 50°C for 15 minutes with mild agitation. After removal of the material from solution, it is allowed to air-dry, then measured in a suitable spectrophotometer to determine CIELAB values. Dye uptake is determined by the L* reading, and changes in dye uptake are found by determining dL* relative to untreated material.

By the term "wool," "wool fiber," "animal hair," and the like, is meant any commercially useful animal hair product, for example, wool from sheep, camel, rabbit, goat, llama, and known as merino wool, shetland wool, cashmere wool, alpaca wool, mohair, etc.

The method of the invention can be used with wool or animal hair material in the form of top, fiber, yarn, or woven or knitted fabric. The enzymatic treatment can also be carried out on loose flock or on garments made from wool or animal hair material. The treatment can be performed at many different stages of processing, including either before or after dyeing. A range of different chemical additives can be added along with the enzymes, including wetting agents and softeners.

It should be emphasized that wool and other animal hair materials are products of biological origin. The material may vary greatly, e.g., in chemical composition and morphological structure depending on the living conditions and health of the animal. Accordingly, the effect(s) obtained by subjecting wool or other animal hair products to the method of the present invention may vary in accordance with the properties of the starting material.

The method of the invention

It is contemplated that enzymatic treatments can take place either as stand-alone steps or in combination with other treatments such as scouring or dyeing of wool or animal hair material. Wool or animal hair material is subjected to treatment with a

transglutaminase either subsequent to or, preferably, simultaneously with a proteolytic enzyme treatment. Further, chemical additives such as surfactants and softeners can be included in enzyme treatment steps, or in separate steps. Such treatments can produce wool textiles having a novel combination of physical properties, such as improved handle, shrink-resistance, and appearance while reducing strength losses and fiber damage commonly observed in degradative treatments of wool.

Treatment conditions. The enzymatic treatment steps are preferably carried out for a duration of at least 1 minute and less than 150 minutes; preferably at a temperature from about 15°C to about 90°C, more preferably from about 20°C to about 70°C, in particular from about 30°C to about 65°C. Alternatively, the wool can be soaked in or padded with an aqueous treatment solution and then subjected to steaming at a conventional temperature and pressure. It is contemplated that the reaction rate of the enzyme treatment step can be increased by increasing the temperature of the enzyme bath during the treatment, i.e., the total treatment time can be reduced.

The enzyme treatment can be carried out in an acidic, neutral or alkaline medium, depending on the particular enzyme in question. The medium may include a buffer. It may be advantageous to carry out the enzyme treatment step in the presence of one or more conventional anionic, non-ionic or cationic surfactants. An example of a useful nonionic surfactant is Dobanol (from Henkel AG).

Proteolytic enzyme

A useful proteolytic enzyme for the method of the present invention is any enzyme having proteolytic activity at the actual process conditions, including a combination of two or more such enzymes. Thus, the enzyme may be a proteolytic enzyme of plant origin, e.g., papain, bromelain, ficin, or of animal origin, e.g. trypsin and chymotrypsin, or of microbial origin, i.e., bacterial or fungal origin or from yeasts. It is to be understood that any mixture of various proteolytic enzyme may be applicable in the process of the invention.

Also, any proteolytic enzyme variant can be used in the process of the present invention, wherein the term "variant" means an enzyme produced by an organism expressing a gene encoding a proteolytic enzyme, and wherein said gene has been obtained by mutation of a naturally occurring proteolytic enzyme gene, the mutation being of either

random or site-directed nature, including the generation of the mutated gene through gene shuffling.

In a preferred embodiment of the invention, the proteolytic enzyme is a serine-protease, a metallo-protease, or an aspartate-protease. A serine protease is an enzyme that catalyzes the hydrolysis of peptide bonds, and contain an essential serine residue at the active site (White, Handler and Smith, 1973 "Principles of Biochemistry," Fifth Edition, McGraw-Hill Book Company, NY, pp. 271-272). They are inhibited by diisopropyl-fluorophosphate, but in contrast to metalloproteases, are resistant to ethylene diamino tetraacetic acid (EDTA) (although they are stabilized at high temperatures by calcium ions).

Serine proteases hydrolyze simple terminal esters and are similar in activity to eukaryotic chymotrypsin, also a serine protease. A more narrow term, alkaline protease, covering a sub-group, reflects the high pH optimum of some of the serine proteases, from pH 9.0 to 11.0. The serine proteases usually exhibit maximum proteolytic activity in the alkaline pH range, whereas the metallo-proteases and the aspartate-proteases usually exhibit maximum proteolytic activity in the neutral and the acidic pH range, respectively.

A sub-group of the serine proteases is commonly designated the subtilases (Siezen *et al.*, *Protein Engng.* 4 (1991) 719-737). They are defined by homology analysis of more than 40 amino acid sequences of serine proteases previously referred to as subtilisin-like proteases. A subtilisin was previously defined as a serine protease produced by Gram-positive bacteria or fungi, and according to Siezen *et al.*, now is a subgroup of the subtilases. The amino acid sequences of a number of subtilases have been determined, including at least six subtilases from *Bacillus* strains, namely, subtilisin 168, subtilisin BPN', subtilisin Carlsberg, subtilisin DY, subtilisin amylosacchariticus, and mesentericopeptidase, one subtilisin from an actinomycetales, thermitase from *Thermoactinomyces vulgaris*, and one fungal subtilisin, proteinase K from *Tritirachium album*. The long time recognized group of serine proteases, the subtilisins, have according to this more recent grouping been divided into two sub-groups. One subgroup, I-S1, comprises the "classical" subtilisins, such as subtilisin 168, subtilisin BPN', subtilisin Carlsberg (ALCALASE®, Novo Nordisk A/S), and subtilisin DY. The other subgroup, I-S2, is described as highly alkaline subtilisins and comprise enzymes such as subtilisin PB92 (MAXACAL®, Genencor International, Inc.), subtilisin 309 (SAVINASE®, Novo Nordisk A/S), subtilisin 147 (ESPERASE®, Novo Nordisk A/S), and alkaline elastase YaB.

These subtilisins of group I-S2 and variants thereof constitute a preferred class of proteases which are useful in the method of the invention. An example of a useful subtilisin variant is a variant of subtilisin 309 (SAVINASE[®]) wherein, in position 195, glycine is substituted by phenylalanine (G195F or ¹⁹⁵Gly to ¹⁹⁵Phe).

Conveniently, conventional fermented commercial proteases are useful. Examples of such commercial proteases are Alcalase[®] (produced by submerged fermentation of a strain of *Bacillus licheniformis*), Esperase[®] (produced by submerged fermentation of an alkalophilic species of *Bacillus*), Rennilase[®] (produced by submerged fermentation of a non-pathogenic strain of *Mucor miehei*), Savinase[®] (produced by submerged fermentation of a genetically modified strain of *Bacillus*), e.g., the variants disclosed in the International Patent Application published as WO 92/19729, and Durazym[®] (a protein-engineered variant of Savinase[®]). All the mentioned commercial proteases are produced and sold by Novo Nordisk A/S, DK-2880 Bagsvaerd, Denmark. Other preferred serine proteases are proteases from *Nocardiopsis*, *Aspergillus*, *Rhizopus*, *Bacillus alcalophilus*, *B. cereus*, *N. natto*, *B. vulgatus*, *B. mycoide*, and subtilins from *Bacillus*, especially proteases from the species *Nocardiopsis sp.* and *Nocardiopsis dassonvillei* such as those disclosed in the International Patent Application published as WO 88/03947, especially proteases from the species *Nocardiopsis sp.*, NRRL 18262, and *Nocardiopsis dassonvillei*, NRRL 18133. Yet other preferred proteases are the serine proteases from mutants of *Bacillus subtilis* disclosed in the International Patent Application Nos. PCT/DK89/00002 and PCT/DK97/00500, and in the International Patent Application published as WO 91/00345, and the proteases disclosed in EP 415 296 A2.

Another preferred class of proteases are the metallo-proteases of microbial origin. Conveniently, conventional fermented commercial proteases are useful. An example of such a commercial protease is Neutrase[®] (Zn) (produced by submerged fermentation of a strain of *Bacillus subtilis*), which is produced and sold by Novo Nordisk A/S, DK-2880 Bagsvaerd, Denmark.

Other useful commercial protease enzyme preparation are Bactosol[™] WO and Bactosol[™] SI, available from Sandoz AG, Basle, Switzerland; Toyozyme[™], available from Toyo Boseki Co. Ltd., Japan; and Proteinase K[™] (produced by submerged fermentation of a strain of *Bacillus sp.* KSM-K16), available from Kao Corporation Ltd., Japan.

The amount of proteolytic enzyme used is preferably in the range 0.001 g to 20 g, preferably in the range 0.01 g to 10 g, more preferably in the range 0.05 g to 5 g per kg wool, fiber, or hair.

Transglutaminase

The "transglutaminase" to be used according to the invention can be any transglutaminase, which includes both calcium-dependent and calcium-independent transglutaminases or mixtures of two or more transglutaminases. Transglutaminases are protein-glutamine γ -glutamyltransferases, and have been classified as enzymes having the number EC 2.3.2.13 according to Enzyme Nomenclature, Academic Press, Inc., 1992. Transglutaminases are enzymes capable of catalyzing an acyl transfer reaction, in which a γ -carboxamide group of a peptide-bound glutamine residue is the acyl donor. Primary amino groups in a variety of compounds may function as acyl acceptors with the subsequent formation of monosubstituted gamma-amides of peptide-bound glutamic acid. When the ϵ -amino group of a lysine residue in a peptide-chain serves as the acyl acceptor, the transglutaminases form intramolecular or intermolecular ϵ -(γ -glutamyl)lysine cross-links.

A wide array of transglutaminases has been identified and isolated from a number of animals and a few plant species. The most widely used animal-derived transglutaminase, Factor XIIIa, is a multi-subunit enzyme.

According to the invention, transglutaminases may be of mammalian origin, such as of human or bovine origin, of marine origin, such as derived from sea squirt (*Halocynthia roretzi*), or of microbial origin, such as of bacterial, yeast or filamentous fungus origin, or variants thereof.

In an embodiment of the invention, the transglutaminase is Factor XIIIa of human origin. In another embodiment, the transglutaminase is a microbial transglutaminase derived from *Streptomyces lydicus* (former *Streptomyces libani*), or variants thereof. Other suitable microbial transglutaminases have been described, including a transglutaminase from *Physarum polycephalum* (Klein et al., Journal of Bacteriology, Vol. 174, pages 2599-2605), as well as transglutaminases from *Streptoverticillium*, in particular from *Streptoverticillium mobaraense*, *Streptoverticillium cinnamoneum*, and *Streptoverticillium griseocar-neum* (Motoki et al., U.S. 5,156,956), and from *Streptomyces lavendulae* (Andou et al., U.S. 5,252,469). The transglutaminases described in EP 481 504-A1 (Amano

Pharmaceutical Co. LTD.) and WO 96/06931 (Novo Nordisk A/S), which are hereby incorporated by references, may also be used. In addition, transglutaminases derived from the class of fungi-like organisms Oomycetes, preferably from the genus *Phytophthora*, may be used. Other relevant Oomycetes transglutaminases are described in PCT/DK96/00031 (Novo Nordisk A/S), which are hereby incorporated by reference. Preferred transglutaminases are *Phytophthora cactorum* and *Streptoverticillium mobaraense* (available from Ajinomoto).

The amount of transglutaminase used is in the range 0.001 g to 10 g, preferably in the range 0.01 g to 5 g, more preferably in the range 0.02 g to 2 g per kg wool, fiber, or hair.

In another embodiment, the transglutaminase is added together with a polyamino-containing compound $R_1NHR_2NHR_3$, wherein R_1 , R_2 , and R_3 can be independently hydrogen, hydrocarbyl, or substituted hydrocarbyl, and any combination of R_1 , R_2 , and R_3 may or may not join together to form one or multiple rings, where the term "hydrocarbyl" means a linear, branched, or cyclic group which contains only carbon and hydrogen atoms; the term "heteroatom" refers to atoms other than carbon and hydrogen; and the term "substituted hydrocarbyl" refers to a hydrocarbyl substituted with one or more heteroatoms. Examples of polyamino-containing compounds are 1,12-diaminododecane and polyethylenimine.

Softeners

It may be desirable to treat the wool or animal hair material with a softening agent, either simultaneously with or after enzymatic treatments. The softeners conventionally used on wool are usually cationic softeners, either organic cationic softeners or silicone-based products, but anionic or non-ionic softeners are also useful. Examples of useful softeners are polyethylene softeners and silicone softeners, i.e., dimethyl polysiloxanes (silicone oils), H-polysiloxanes, silicone elastomers, aminofunctional dimethyl polysiloxanes, aminofunctional silicone elastomers, and epoxyfunctional dimethyl polysiloxanes, and organic cationic softeners, e.g., alkyl quarternary ammonium derivatives.

The invention is further illustrated in the following non-limiting examples.

Examples

Example 1. Treatment with Transglutaminase and Protease

Swatches (24 cm x 24 cm, with 18 x 18 cm² rectangle inscribed on each, approximately 9 g each) of jersey knit wool (TestFabrics TF532) were sewn around the edges. Samples were placed in separate Launder-O-meter beakers containing 250 mL of a 0.04 M Tris buffer, pH 8.25 at 25°C, containing 5 mM calcium chloride. A solution of ESPERASE® 8.0 L (200 µl) was added to the vessels, followed immediately by a solution of *Phytophthora cactorum* transglutaminase (containing 4 mg transglutaminase). The vessels were placed in the Launder-O-meter and allowed to react for 40 minutes at 44°C, followed by a ten minute heating gradient up to 80°C, then held at that temperature for ten minutes to inactivate the enzymes. The sample was removed from the solution, rinsed, dried, and measured, then subjected to five cycles of machine washing and drying, before being subjected to further property testing.

Example 2. Treatment with Haloperoxidase, Savinase, and Transglutaminase

Two swatches (24 cm x 24 cm, with 18 x 18 cm² rectangle inscribed on each, approximately 9 g each) of jersey knit wool (TestFabrics TF532) were sewn around the edges. The swatches were immersed in 500 ml of a 25 mM sodium acetate buffer containing 10 mM NaCl and 10 mM hydrogen peroxide, pH 5, and treated with *Curvularia verruculosa* haloperoxidase (3.3 mg pure enzyme) for 50 minutes at 40°C in an incubating shaker bath. After 30 minutes, sufficient hydrogen peroxide was added to boost the depleted peroxide concentration by 5 mM. Samples were rinsed and allowed to air-dry, then placed in separate Launder-O-meter beakers containing 250 ml of a 0.04 M Tris buffer, pH 8.25 at 25°C, containing 5 mM calcium chloride. A solution of SAVINASE® 16.0L (200 µl) was added to the vessels, followed immediately by a solution of *Phytophthora cactorum* transglutaminase (containing 6 mg transglutaminase). The vessels were placed in the Launder-O-meter and allowed to react for 40 minutes at 44°C, followed by a ten minute heating gradient up to 80°C, then held at that temperature for ten minutes to inactivate the enzyme. The sample was removed from the solution, rinsed, dried, and measured, then subjected to five cycles of machine washing and drying, before being subjected to further property testing.

Example 3. Treatment with Haloperoxidase, Esperase, and Transglutaminase

Two swatches (24 cm x 24 cm, with 18 x 18 cm² rectangle inscribed on each, approximately 9 g each) of jersey knit wool (TestFabrics TF532) were sewn around the edges. The swatches were immersed in 500 ml of a 25 mM sodium acetate buffer containing 10 mM NaCl and 10 mM hydrogen peroxide, pH 5, and treated with *Curvularia verruculosa* haloperoxidase (3.3 mg pure enzyme) for 50 minutes at 40°C in an incubating shaker bath. After 30 minutes, sufficient hydrogen peroxide was added to boost the depleted peroxide concentration by 5 mM. Samples were rinsed and allowed to air-dry, then placed in separate Launder-O-meter beakers containing 250 ml of a 0.04 M Tris buffer, pH 8.25 at 25°C, containing 5 mM calcium chloride. A solution of ESPERASE® 8.0L (200 µL) was added to the vessels, followed immediately by a solution of *Phytophthora cactorum* transglutaminase (containing 6 mg transglutaminase). The vessels were placed in the Launder-O-meter and allowed to react for 40 minutes at 44°C, followed by a ten minute heating gradient up to 80°C, then held at that temperature for ten minutes to inactivate the enzyme. The sample was removed from the solution, rinsed, dried, and measured, then subjected to five cycles of machine washing and drying, before being subjected to further property testing.

Example 4. Treatment with Haloperoxidase, Esperase, and Transglutaminase

Two swatches (24 cm x 24 cm, with 18 x 18 cm² rectangle inscribed on each, approximately 9 g each) of jersey knit wool (TestFabrics TF532) were sewn around the edges. The swatches were immersed in 500 ml of a 25 mM sodium acetate buffer containing 10 mM NaCl and 10 mM hydrogen peroxide, pH 5, and treated with *Curvularia verruculosa* haloperoxidase (3.3 mg pure enzyme) for 50 minutes at 40°C in an incubating shaker bath. After 30 minutes, sufficient hydrogen peroxide was added to boost the depleted peroxide concentration by 5 mM. Samples were rinsed and allowed to air-dry, then placed in separate Launder-O-meter beakers containing 250 ml of a 0.04 M Tris buffer, pH 8.25 at 25°C, containing 5 mM calcium chloride. A solution of ESPERASE® 8.0L (200 µL) was added to the vessels, followed immediately by a solution of *Streptover-ticillium mobaraense* transglutaminase (Ajinomoto)(containing 0.9 mg transglutaminase). The vessels were placed in the Launder-O-meter and allowed to react for 40 minutes at

44°C, followed by a ten minute heating gradient up to 80°C, then held at that temperature for ten minutes to inactivate the enzyme. The sample was removed from the solution, rinsed, dried, and measured, then subjected to five cycles of machine washing and drying, before being subjected to further property testing.

The sample had a very soft handle, a pleasing appearance as a result of increased whitening and reduced pilling, and an area shrinkage of only 12% after five wash-dry cycles, corresponding to a shrink-resistance of 64%.

Example 5. Treatment with Sodium hypochlorite, Savinase, and Transglutaminase.

A swatch (24 cm x 24 cm, with inscribed 18 x 18 cm² rectangle, approximately 9 g) of jersey knit wool (TestFabrics TF532) was sewn around the edges. The swatch was immersed in 250 ml of a 25 mM sodium acetate buffer containing 10 mM NaCl, pH 5, and treated with 1.5 ml of a commercial solution of sodium hypochlorite (Austin's® bleach, 5.25% sodium hypochlorite). The reaction was allowed to proceed for 50 minutes at 40°C in a Launder-O-meter, at which point the fabric was removed from solution and rinsed with water, then placed in a Launder-O-meter beaker containing 250 ml of a 0.04 M Tris buffer, 5 mM calcium chloride, pH 8.35 at 25°C. A solution of SAVINASE® 16.0L (200 µL) was added to the vessels, followed immediately by a solution of *Phytophthora cactorum* transglutaminase (containing 6 mg transglutaminase). The vessels were placed in the Launder-O-meter and allowed to react for 40 minutes at 44°C, followed by a ten minute heating gradient up to 80°C, then held at that temperature for ten minutes to inactivate the enzyme. The sample was removed from the solution, rinsed, dried, and measured, then subjected to five cycles of machine washing and drying, before being subjected to further property testing.

Example 6. Weight loss, burst strength, and shrinkage of wool treated with Protease and Transglutaminase

Wool swatches were subjected to a combined protease and transglutaminase treatment. The samples were thoroughly rinsed, wrung dry, then subjected to six machine wash/dry cycles, (two with cold wash and hot drying, four with warm wash and high heat drying), equilibrated in a constant temperature and humidity room, then tested.

Experimental Conditions: Material: Wool swatches (jersey knit wool -

TestFabrics TF532), 24 cm x 24 cm, with 18 x 18 cm² rectangle inscribed on each, approximately 9 g each, sewn around the edges.

Treatment Conditions: Wool swatches were incubated individually in Launder-O-meter vessels in 250 mL buffer (40 mM Tris, pH 8.25 at 25°C) containing the specified amounts of Esperase 8.0L and *Phytophthora cactorum* transglutaminase solution (approximately 4% protein by weight in solution); for 40 minutes at 44°C, ramped up to 80°C over ten minutes, then held at 80°C for ten minutes.

Sample	Esperase	TG	Weight Loss	Strength	Shrinkage
	(mL)	(μL)	(%)	(lb/sq. in.)	(%)
1	0	0	-0.61	55.0	30.2
2	0	50	-0.41	53.3	28.8
3	0	200	-0.45	53.0	28.0
4	0	1000	-0.52	53.0	29.2
5	1	0	-2.63	52.7	22.3
6	1	50	-2.93	50.0	24.2
7	1	100	-2.52	53.7	17.0
8	1	200	-2.87	48.7	18.8
9	1	400	-2.78	53.3	20.6

Note: Weight loss was measured after six wash-dry cycles. Shrinkage is measured after six machine wash/dry cycles. "Strength" is a measure of the dry burst strength of the wool fabric, with several tests per swatch.

As is apparent from the above data table, a combination treatment using the optimum concentration of transglutaminase yields wool with reduced fiber damage (as manifested in decreased weight loss and increased burst strength) and increased shrink-resistance relative to wool treated exclusively with protease. Furthermore, the data indicate that treatment with transglutaminase alone does not provide significant benefits.

It should be pointed out that transglutaminase is a cross-linking enzyme. It is critical to optimize the extent of cross-linking for every different set of reaction conditions, as too much cross-linking results in brittle, weak fibers. Thus, the optimized level of transglutaminase identified in this example is for a given transglutaminase, for use with the specified quantity of Esperase®, at the specified temperature and time, with the specified wool. It is clear that changes in reaction conditions require changes in the optimal amount of transglutaminase (and obviously not all transglutaminases behave the same). Thus, we are unable to identify a universal preferred concentration ratio for all combination of proteases and transglutaminases under all possible reaction conditions.

Example 7. Weight loss, burst strength, whiteness and shrinkage of wool treated with Protease and Transglutaminase following a mild oxidative treatment

Wool swatches were subjected to a mild oxidative chlorination step using an acidified solution of sodium hypochlorite, then rinsed, wrung dry, and subjected to a combined protease and transglutaminase treatment. The samples were thoroughly rinsed, wrung dry, subjected to five machine wash/dry cycles (warm wash, high heat drying), equilibrated in a constant temperature and humidity room, then tested.

Experimental Conditions: Material: Wool swatches (jersey knit wool - TestFabrics TF532), 24 cm x 24 cm, with 18 x 18 cm² rectangle inscribed on each, approximately 9 g each, sewn around the edges.

Pre-Treatment Conditions: Wool swatches were incubated in pairs in Launder-O-Meter vessels with 500 mL buffer (25 mM sodium acetate, pH 5.0 at 25°C) containing 1 mL of commercial household bleach solution (5.25 % sodium hypochlorite by weight) for 45 minutes at 40°C.

Treatment Conditions: Wool swatches were incubated in pairs in Launder-O-Meter vessels with 500 mL buffer (40 mM Tris, pH 8.30 at 25°C) containing 0.4 mL Savinase 16.0L and the indicated amount of *Phytophthora cactorum* transglutaminase solution (approximately 4 % protein by weight in solution); for 40 minutes at 54°C, ramped up to 80°C over ten minutes, then held at 80°C for ten minutes.

<u>Sample</u>	<u>Savinase</u>	<u>Temp.</u>	<u>TG</u>	<u>Weight Loss</u>	<u>Strength</u>	<u>Shrinkage</u>	<u>Whiteness</u>
	(mL)	(°C)	(μL)	(%)	(lb/sq. in.)	(%)	(W)
1	0	44	0	-0.18	36.7	30.0	-2.5
2	0.2	54	0	5.45	33.5	23.0	3.5
3	0.2	54	100	4.88	33.6	17.0	4.7
4	0.2	54	200	4.95	33.8	15.8	6.3

Note: All values represent the average of two runs. Reactant concentrations are per wool swatch. Weight loss was measured after six wash-dry cycles. Shrinkage was measured after five machine wash/dry cycles. "Strength" is a measure of the wet burst strength of the wool fabric, with several tests per swatch. Whiteness (in Stensby units) was measured after 5 wash-dry cycles.

After a mild oxidative chlorination pre-treatment, treatment of wool with a selected combination of protease and transglutaminase gives superior shrink-resistance and whiteness relative to untreated or protease-treated wool, while conserving weight and strength losses relative to treatments with protease alone.

CLAIMS

We claim:

1. A method of treating wool, wool fibers or animal hair, comprising contacting the wool, fibers or hair in aqueous solution with an effective amount of (i) a proteolytic enzyme, and (ii) a transglutaminase.
2. The method of claim 1, wherein the wool, wool fiber, or animal hair is treated simultaneously with a proteolytic enzyme and a transglutaminase.
3. The method of claim 1, wherein the wool, wool fiber, or animal hair is treated with a transglutaminase following treatment with a proteolytic enzyme.
4. The method of claim 1, wherein the proteolytic enzyme is of plant, animal, bacterial, or fungal origin.
5. The method of claim 4, wherein the proteolytic enzyme is selected from the group consisting of papain, bromelain, ficin, and trypsin.
6. The method of claim 4, wherein the proteolytic enzyme is a serine protease.
7. The method of claim 6, wherein the serine protease is a subtilisin derived from *Bacillus* or *Tritirachium*.
8. The method of claim 1, wherein the amount of protease used per kg wool, fiber, or hair is in the range 0.001 g to 10 g.
9. The method of claim 1, wherein the transglutaminase is derived from *Streptoverticillium*.
10. The method of claim 1, wherein the transglutaminase is derived from *Phytophthora*.

11. The method of claim 1, wherein the human transglutaminase is Factor XIIIa.
12. The method of claim 1, wherein the transglutaminase is added along with a polyamino-containing compound $R_1NHR_2NHR_3$, wherein R_1 , R_2 , and R_3 can be independently hydrogen, hydrocarbyl, or substituted hydrocarbyl, and any combination of R_1 , R_2 , and R_3 may join together to form one or multiple rings.
13. The method of claim 12, wherein the polyamino-containing compound is polyethylenimine.
14. The method of claim 1, wherein the amount of transglutaminase used per kg wool, fiber, or hair is in the range 0.001 g to 10 g.
15. The method of claim 1, wherein the aqueous solution additionally comprises a softening agent.
16. The method of claim 1, wherein the wool, wool fibers or animal hair are treated with a softening agent after the protease and transglutaminase treatment.
17. The method of claim 1, wherein the wool, wool fibers, or animal hair are subjected to an oxidative treatment prior to said treatment with protease and transglutaminase.
18. The method of claim 17, wherein said oxidative treatment is an oxidative chlorination.
19. The method of claim 17, wherein said oxidative treatment comprises enzymatic treatment with an oxidoreductase.
20. The method of claim 19, wherein said oxidoreductase is a haloperoxidase.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/10496

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 D06M16/00 //D06M101:12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 D06M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>DATABASE WPI Section Ch, Week 9144 Derwent Publications Ltd., London, GB; Class D16, AN 91-320726 XP002113322 & JP 03 213574 A (AJINOMOTO KK), 18 September 1991 (1991-09-18) cited in the application abstract</p> <p style="text-align: center;">--- -/-</p>	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

25 August 1999

Date of mailing of the international search report

03/09/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Blas, V

INTERNATIONAL SEARCH REPORT

Int'l Patent Application No
PCT/US 99/10496

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	HEINE E ET AL: "ENZYME TREATMENTS FOR WOOL AND COTTON" REVIEW OF PROGRESS IN COLORATION & RELATED TOPICS, vol. 25, 1 January 1995 (1995-01-01), pages 57-63, XP000537256 ISSN: 0557-9325 page 58, paragraph dealing with "Shrinkproofing" - page 60, end first column ----	1-6, 8, 17, 18
A	WO 96 19611 A (HEINE ELISABETH ;HOECKER HARTWIG (DE); DYBDAL LONE (DK); NOVONORDI) 27 June 1996 (1996-06-27) page 13, line 21 - page 17, line 7 ----	1-8, 15-17
A	EP 0 134 267 A (KURASHIKI BOSEKI KK) 20 March 1985 (1985-03-20) cited in the application the whole document ----	1-8, 17, 18
A	FORNELLI S: "ENZYMATIC TREATMENT OF PROTEIN FIBRES - STATE-OF-THE-ART BIOTECHNOLOGY" INTERNATIONAL DYER, vol. 178, no. 10, 1 October 1993 (1993-10-01), page 29, 31, 33 XP000396676 ISSN: 0020-658X the whole document -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/10496

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 3213574 A	18-09-1991	NONE	
WO 9619611 A	27-06-1996	AU 4298696 A	10-07-1996
		BR 9510216 A	04-11-1997
		CN 1170448 A	14-01-1998
		EP 0799344 A	08-10-1997
		HU 77196 A	02-03-1998
		JP 10511437 T	04-11-1998
		PL 321426 A	08-12-1997
		TR 960604 A	21-07-1996
EP 0134267 A	20-03-1985	JP 1054471 B	20-11-1989
		JP 1581565 C	11-10-1990
		JP 58144105 A	27-08-1983
		US 4533359 A	06-08-1985